



Isothane Elastomer D765 Polyurethane Elastomer

PRODUCT DESCRIPTION

Isothane Elastomer D765 is a polyether based resin system which, when combined with Isothane M15 Prepolymer, will produce a polyurethane elastomer of 65-70°D hardness. Elastomer D765 is cold castable, free from MOCA, mercury based catalysts, TDI and flammable solvents.

Elastomer D765 can be readily processed and cured at room or elevated temperatures. The convenient mix ratio and low viscosity allow easy processing.

USES

Elastomer D765 is suitable for most moulding and casting applications. Typical uses include the production of medium sized castings and medium dimension mould production. The products excellent resistance to hydrolysis lends itself to marine and other wet environment uses.

TYPICAL PROPERTIES

	Elastomer D765	M15 PREPOLYMER
Appearance	Free flowing liquid	Pale brown liquid
Viscosity @ 25°C (cPs)	300 – 500	130 -170
Specific Gravity	1.01 – 1.06	1.20 – 1.24
%NCO	-	26

PROCESSING

Elastomer D765	(pbw)	100
M15 Prepolymer	(pbw)	78
Elastomer D765 Temperature	(°C)	25-30
M15 Prepolymer Temperature	(°C)	25-30
Mixed Viscosity @ 25°C	(cPs)	2500
Pot Life at 25°C	(mins)	9-13
Cure at 25°C		72 hours at 25°C Accelerated cure of 16 hours at 70°C
Optimum mould temperature	(°C)	80

The system may be processed either by hand mixing with a drill stirrer, or by dispensing through specially designed equipment having accurate metering pumps for the two components and a suitable mixing head. The components should be maintained at a minimum of 20°C and should be mixed immediately before the intended pouring process. When hand-mixing the product should be thoroughly degassed under vacuum before curing.

Isothane Limited, Unit 10, Newhouse Road, Huncoast Industrial Estate, Accrington, Lancashire BB5 6NT
Telephone 01254 872555 Fax 01254 871522 Order Line Fax 01254 398295

Email info@isothane.com Website www.isothane.com





In applications where bonding of the product to other material is a requirement, use of a primer from the Isothane range may be necessary to maximise adhesion.

It is important to note that components of the resin formulation may separate on standing and the material should be agitated before use in order to effect re-dispersion. If during re-dispersion air is mixed into the resin, it must be degassed before use.

CURED ELASTOMER PROPERTIES

		<u>Typical Values</u>	<u>Test Method</u>
Hardness	(Shore D)	65-70	BS2782
Tensile Strength	(MPa)	24	BS903
Elongation	(%)	200	BS903
Tear Strength	(KN/m)	187	BS903
Density		1.12	BS903
Coefficient of Linear Expansion		150x10 ⁻⁶	ASTM D696

STORAGE, HANDLING AND PERSONAL PROTECTION

Elastomer D765 and M15 prepolymer should be stored in dry conditions at 20-25°C. Opened or part used containers must be resealed immediately after use and capped with dry air or nitrogen where possible.

If Elastomer D765 has been stored in cold conditions for long periods it should be heated to 30-40°C then thoroughly agitated and cooled to 20-25°C before use. Cold M15 Prepolymer should be heated to 70-80°C to allow melt out, then thoroughly agitated and cooled to 20-25°C before use.

The shelf life for the unopened product is 6 months. The recommendations in our Safety Data Sheet for this product must be followed at all times. More general information is included in our publication "A Guide to the Safe Handling of Polyurethane Chemicals" and in "Decontamination of Isocyanates using Isothane Decontaminant".

The recommendations in the Elastomer D765 and M15 Prepolymer safety data sheets should be followed at all times.

This information is of a general nature and is supplied without recommendation or guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Liability for loss or damage through use cannot be accepted except for death or injury caused by negligence on the part of Isothane Ltd. Whilst these specifications are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are applied. Users must, by comprehensive testing, ensure suitability of product for own use. Without control or supervision of the preparation for and application of Isothane products, general guarantees cannot be offered.

Isothane Limited, Unit 10, Newhouse Road, Huncoast Industrial Estate, Accrington, Lancashire BB5 6NT
Telephone 01254 872555 Fax 01254 871522 Order Line Fax 01254 398295

Email info@isothane.com Website www.isothane.com

